



Treo™ Smooth

1-800-UNILOCK | [UNILOCK.COM](https://www.uni-lock.com)

UNILOCK
PAVERS & WALLS

TREO[®] SMOOTH

CLASSIC  PERMEABLE

NEW FOR 2021



GRANITE BLEND

PRODUCT ATTRIBUTES

Visual Appearance	Treo Smooth offers a smooth surface texture for a sleek, modern look with a contemporary colour palette.
Finish	Smooth, classic appearance.

PRODUCT SPECIFICATIONS



LARGE RECTANGLE
8 7/8" x 13 1/2" x 3 1/8"
226 x 343 x 80mm



SQUARE
8 7/8" x 8 7/8" x 3 1/8"
226 x 226 x 80mm



SMALL RECTANGLE
4 1/4" x 8 7/8" x 3 1/8"
110 x 226 x 80mm

3 UNIT RANDOM BUNDLE

EDGE DETAILS



ROUNDED EDGE

RECOMMENDED SAND



Gator G2 MAXX Sand

- | Setting time - 15 mins
- | Sets above 32° F/ 0° C
- | Can be applied if rain is expected (min. 1 hr)
- | Dust free and haze free
- | Requires only one watering
- | Four colours: Beige, Grey, Black and Ivory

Coverage:

Colour	Narrow Joints	Wide Joints
Beige, Grey, Ivory <i>50lb. bag</i>	65-85 sqft	22-42 sqft
Black <i>50lb. bag</i>	58-76 sqft	20-38 sqft

RECOMMENDED SEALER



Gator Natural Look Sealer

- | Water-based
- | Zero gloss finish
- | Multi purpose
- | Rain safe after 24 hours

Coverage:

Size	Area
3.78 L / 1 U.S. gal.	175 sqft
18.9 L. / 5.28 U.S. gal.	875 sqft

TECHNICAL INFORMATION

ASTM C 936 Standard Specifications for Solid Concrete Interlocking Paving Units

Conforms to:

- C140 for Absorption 5% avg - 7% max
- Compressive Strength > 7,200 PSI avg.
- C67 for Freeze-thaw Durability
- C418 for Abrasion Durability
- Dimensional Accuracy +/- 3mm

Test results available upon request

Meets the U.S. Architectural & Transportation Barrier Compliance Board Slip-Resistance Surfaces Advisory Guidelines

LEED INFORMATION

Materials & Resources: LEED V4:

Building Product Disclosure and Optimization

Sourcing of Raw Materials - Sourcing of Raw Materials and Extraction • 1 point

Sourcing of Raw Materials - Leadership Extraction Practices • 1 point

Material Ingredient Reporting - Material Ingredient Reporting • 1 point

Material Ingredient Reporting - Material Ingredient Optimization • 1 point

Environmental Product Declaration • 1 point

TECHNICAL ADVANTAGES

CLASSIC

Budget-friendly. Utilize a traditional product mix of large and small aggregates that's consistent from top to bottom with colour mixed throughout



PERMEABLE

Can be installed to allow water to flow through

DRIVE FRIENDLY

Can handle vehicular loads

Ask about our base stabilization system

PRODUCT DATA

Stones & Bundling	Unit Thickness	SqFt Per				Per Bundle		Soldier LnFt Per			Sailor LnFt per			Units Per		Lbs Per		
		Bundle	Layer	Section	Stone	Layers	Section	Unit	Section	Bundle	SqFt	Layer	Bundle	SqFt	Bundle	Layer	Section	Bundle
Ayr Manufacturing																		
Random Bundle		93.50	11.69			8	-	-	-	-	-		74.4	0.77	168	427.63	-	3,421
Large Rectangle	3 1/8" (80mm)	42.07	5.259	-		8	-	-	-	-	-		24.8	0.48	48	192.45	-	1,539.64
Square	3 1/8" (80mm)	32.72	4.091	-		8	-	-	-	-	-		24.8	0.72	56	149.69	-	1,197.50
Small Rectangle	3 1/8" (80mm)	18.70	2.337	-		8	-	-	-	-	-		24.8	1.43	64	85.54	-	684.29

Notes: Sold in full bundles only on a refundable skid. All measurements are nominal. **Important: A urethane rubber paver mat must be used to prevent scuffing.** Contact your Unilock Territory Manager or call 1-800-UNILOCK for further information. *For custom options, please contact your Unilock Territory Manager.

APPLICATIONS



Pedestrian



Wall pairing suggestion- U-CARA - matching colour and finish



Residential Vehicular



Commercial Vehicular

*Paver Maintenance Tips:

- Equip plow scrapers and blades with shoes or high-density plastic blades to reduce the risk of damaging paver joints and the surface
- Only apply min. amount of de-icing salts necessary to melt the snow and ice. Remove excess salt after ice melts
- Regular cleaning routine should include sweeping or blowing loose debris from the pavement surface, and less frequently, deep cleaning with cleaning products and/or water
- Unilock pavers do not require sealing, however, some people choose to do so for aesthetic purposes

*Things to know:

Efflorescence is a naturally occurring calcium salt that can sometimes appear on the surface of concrete and clay products. Efflorescence does not affect the structural integrity of concrete, it is a purely aesthetic issue that typically disappears with no further intervention after a season of rainfall. If desired, the process can be accelerated by washing the surface with an Efflorescence Remover.



For Permeable applications- it is recommended that the jointing material be regularly maintained, including vacuuming, cleaning and reapplying to keep infiltration at its maximum potential.